

# COVERAGE TABLES

## REQUIREMENTS FOR FILLING JOINT SLOTS (LINEAL FT/GAL.)

Width (in.)	1/4	1/2	3/4	1	1-1/4	1-1/2
1/4	308.0					
1/2	154.0	77.0				
3/4	102.7	51.3	34.2			
1	77.0	38.5	25.7	19.3		
1-1/4	61.6	30.8	20.5	15.4	12.3	
1-1/2	51.3	25.7	17.1	12.8	10.3	8.6
1-3/4	44.0	22.0	14.7	11.0	8.8	7.3
2	38.5	19.3	12.8	9.6	7.7	6.4
2-1/4	30.8	15.4	10.3	7.7	6.2	5.1
2-1/2	25.7	12.8	8.6	6.4	5.1	4.3

## (THEORETICAL) COVERAGES FOR COATING OR MEMBRANES

Thickness of coating applied (1000 mils = 1 in)	Coverage per US Gallon 100% Solid System
1/4 in. = 250.000 mils	6.4 sq. ft.
3/16 in. = 187.500 mils	8.5 sq. ft.
1/8 in. = 125.000 mils	12.8 sq. ft.
100.000 mils	16.0 sq. ft.
1/16 in. = 62.500 mils	25.7 sq. ft.
50.000 mils	32.1 sq. ft.
1/32 in. = 32.250 mils	51.3 sq.ft
20.000 mils	80.2 sq.ft.
1/64 in. = 15.625 mils	102.7 sq.ft.
10.000 mils	160.4 sq.ft
5.000 mils	320.8 sq. ft.
1.000 mils	1604.2 sq. ft.

**Note:** If a coating contains a solvent which evaporates, the thickness of the coating will be reduced by the same percentage as the solvent loss.