

# FIBERMESH® 300

## PRODUCT DATA SHEET



### SPECIFY FIBERMESH® 300 FIBERS:

- REDUCED PLASTIC SHRINKAGE CRACKING
- ALTERNATIVE TO TRADITIONAL REINFORCEMENT
- IMPROVED IMPACT, SHATTER AND ABRASION RESISTANCE
- IMPROVED RESIDUAL STRENGTH
- REDUCED WATER MIGRATION AND DAMAGE FROM FREEZE/THAW
- IMPROVED DURABILITY
- AREAS REQUIRING NON-METALLIC MATERIALS



### FIBERMESH® 300 SYNTHETIC FIBER

Fibermesh 300, formerly InForce™ e3,® micro-reinforcement system for concrete—100 percent virgin homopolymer polypropylene fibrillated fibers with e3® patented technology containing no reprocessed olefin materials. Specifically engineered and manufactured in an ISO 9001:2000 certified facility to an optimum gradation for use as concrete secondary reinforcement at a minimum of 0.1% by volume (1.5 lbs/yd<sup>3</sup>, 0.9 kg/m<sup>3</sup>). UL Classified. Complies with National Building Codes and ASTM C III6/C III6M, Type III fiber reinforced concrete.

### ADVANTAGES

Accepted by National Codes as an alternate method of secondary reinforcing to traditional systems • Non-magnetic • Rustproof • Alkali proof • Requires no minimum amount of concrete cover • Is always positioned in compliance with codes • Safe and easy to use • Saves time and hassle

### FEATURES & BENEFITS

- Alternate system to welded wire reinforcement for secondary reinforcing in concrete
- Inhibits and controls the formation of intrinsic cracking in concrete
- Reinforces against impact forces
- Reinforces against the effect of shattering forces
- Reinforces against material loss from abrading forces
- Reinforces against water migration
- Provides improved durability
- Imparts toughness to hardened concrete
- Reduces plastic shrinkage and settlement cracking
- Provides residual strength

### PRIMARY APPLICATIONS

Applicable to all types of concrete which demonstrate a need for toughness, resistance to intrinsic cracking and improved water tightness.

- Slabs-on-ground
- Composite metal decks
- Driveways
- Stucco
- Sidewalks
- Shotcrete
- Curbs
- Slope paving
- Overlays & toppings

### CHEMICAL AND PHYSICAL PROPERTIES

Absorption	Nil	Melt Point	324°F (162°C)
Specific Gravity	0.91	Ignition Point	1100°F (593°C)
Fiber Length*	Graded	Thermal Conductivity	Low
Electrical Conductivity	Low	Alkali Resistance	Alkali Proof
Acid & Salt Resistance	High		

\*Also available in single cut lengths

# FIBERMESH<sup>®</sup> 300

## PRODUCT DATA SHEET

### PRODUCT USE

**MIXING DESIGNS AND PROCEDURES:** Fibermesh<sup>®</sup> 300 microreinforcing is a mechanical, not chemical, process. The addition of Fibermesh 300 fibrillated fiber does not require any additional water or other mix design changes at normal rates. Fibermesh 300 fibrillated fiber is added to the mixer before, during or after batching the other concrete materials. Mixing time and speed are specified in ASTM C 94.

**FINISHING:** Fibermesh 300 micro-reinforced concrete can be finished by any finishing technique. Exposed aggregate, broomed and tined surfaces are no problem.

**APPLICATION RATE:** The standard application rate for Fibermesh 300 fibrillated fibers is 1.5 lbs/yd<sup>3</sup> (0.9 kg/m<sup>3</sup>). For specialty performance see your local Fibermesh representative for recommendations regarding increased application rates.

### GUIDELINES

Fibermesh 300 fibers should not be used to replace structural, loadbearing reinforcement. Fibermesh 300 fibers should not be used as a means of using thinner concrete sections than original design. Fibermesh 300 fibers should not be used to increase joint spacing past those dimensions suggested by PCA and ACI industry standard guidelines.

### COMPATIBILITY

Fibermesh 300 fibers are compatible with all concrete admixtures and performance enhancing chemicals, but require no admixtures to work.

### PACKAGING

Fibermesh 300 fibers are available in a variety of packaging options. The 1.5 lb bag (1 bag per cubic yard, 0.9 kg/m<sup>3</sup>) is standard. Special packaging is available for full truckload addition. Bags are packed into cartons, shrink-wrapped and palletized for protection during shipping.

### TECHNICAL SERVICES

Trained Propex Concrete Systems specialists are available worldwide to assist and advise in specifications and field service. Propex Concrete Systems representatives do not engage in the practice of engineering or supervision of projects and are available solely for service and support of our customers.



Propex<sup>™</sup> Fibermesh<sup>®</sup>

#### NORTH AMERICA

Propex Operating Company, LLC  
6025 Lee Highway, Suite 425  
Chattanooga, TN 37421  
Tel: 800 621 1273  
Tel: 423 892 8080  
Fax: 423 892 0157

#### INTERNATIONAL

Propex Concrete Systems Ltd.  
Propex House  
9 Royal Court, Basil Close  
Chesterfield, Derbyshire, S41 7SL  
United Kingdom  
Tel: +44 (0) 1246 564200  
Fax: +44 (0) 1246 465201

### REFERENCE DOCUMENTS

- ASTM C 94/C 94M Standard Specification for Ready-Mixed Concrete.
- ASTM C 1116/C 1116M Standard Specification for Fiber-Reinforced Concrete.
- ASTM C 1399 Standard Test Method for Obtaining Average Residual-Strength of Fiber-Reinforced Concrete.
- ASTM C 1436 Standard Specification for Materials for Shotcrete.
- ASTM C 1609/C 1609M Standard Test Method for Flexural Performance of Fiber-Reinforced Concrete (Using Beam With Third-Point Loading). Replaces ASTM C 1018.
- ACI 304 Guide for Measuring, Mixing, Transporting and Placing Concrete.
- ACI 506 Guide for Shotcrete.
- International Code Council (ICC) NER-414 Evaluation Report.



UL<sup>®</sup> Classified: Type Fibermesh 300 fiber. For use as an alternate or in addition to the welded wire fabric used in Floor-Ceiling D700, D800, D900 Series Designs. Fiber may also be used in Floor-Ceiling Design Nos. G229, G243, G256, G514. Fibers added to concrete mix at a rate of 1.5 lb of fiber for each cubic yard of concrete.

### SPECIFICATION CLAUSE

Use only Fibermesh 300 - 100 percent virgin polypropylene fibrillated fibers with e3<sup>®</sup> patented technology containing no reprocessed olefin materials and specifically manufactured to an optimum gradation for use as concrete secondary reinforcement. Application per cubic yard shall equal a minimum of 0.1% by volume (1.5 lbs/yd<sup>3</sup>, 0.9 kg/m<sup>3</sup>). Fibermesh 300 fibers are for the control of cracking due to drying shrinkage and thermal expansion/contraction, lowered water migration, increased impact capacity, shatter resistance, abrasion resistance and residual strength. Fiber manufacturer shall document evidence of ten year satisfactory performance history, ISO 9001:2000 certification of manufacturing facility, compliance with applicable building codes and ASTM C 1116/C 1116M, Type III fiber reinforced concrete. Fibrous concrete reinforcement shall be manufactured by Propex Operating Company, LLC, 6025 Lee Highway, Suite 425, PO Box 22788, Chattanooga, TN 37422, USA, tel: 423 892 8080, fax: 423 892 0157, web site: fibermesh.com.

Fibermesh<sup>®</sup>, Novomesh<sup>®</sup>, Novocan<sup>®</sup>, ENDURO<sup>®</sup>, Fibercast<sup>®</sup> and e3<sup>®</sup> are registered trademarks of Propex Concrete Systems Corp. THIS PUBLICATION SHOULD NOT BE CONSTRUED AS ENGINEERING ADVICE. WHILE INFORMATION CONTAINED IN THIS PUBLICATION IS ACCURATE TO THE BEST OF OUR KNOWLEDGE, PROPEX DOES NOT WARRANT ITS ACCURACY OR COMPLETENESS. THE ULTIMATE CUSTOMER AND USER OF THE PRODUCTS SHOULD ASSUME SOLE RESPONSIBILITY FOR THE FINAL DETERMINATION OF THE SUITABILITY OF THE INFORMATION AND THE PRODUCTS FOR THE CONTEMPLATED AND ACTUAL USE. THE ONLY WARRANTY MADE BY PROPEX FOR ITS PRODUCTS IS SET FORTH IN OUR PRODUCT DATA SHEETS FOR THE PRODUCT, OR SUCH OTHER WRITTEN WARRANTY AS MAY BE AGREED BY PROPEX AND INDIVIDUAL CUSTOMERS. PROPEX SPECIFICALLY DISCLAIMS ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ARISING FROM PROVISION OF SAMPLES, A COURSE OF DEALING OR USAGE OF TRADE.

©2012 Propex Operating Company, LLC  
05/12