



# MASCO CURE & SEAL WB



## **BENEFITS:**

- **Non-Yellowing**
- **Dries & Stays Clear**
- **Low Odor**
- **Interior/ Exterior Use**
- **Water Cleanup**
- **UV Resistant**
- **Economical**
- **V.O.C. Compliant**
- **Meets ASTM-C-309**

*The Clear Choice!*

MASONS SUPPLY COMPANY • P.O. Box 42367 • Portland, OR 97242 • 503-234-4321 • Fax 503-234-5606  
MASONS SUPPLY COMPANY • 6018-234th St. SE • Woodinville, WA 98072 • 425-487-6161 • Fax 425-402-3676

**Offering the largest inventory of masonry and concrete accessories in the Pacific Northwest.**



# MASCOCURE CURE & SEAL WB

## DESCRIPTION

MASCOCURE CURE & SEAL WB is a water-emulsion acrylic ready-to-use compound for curing, sealing, and dustproofing concrete. Once properly applied, it provides an impermeable seal to prevent the rapid evaporation of water from the surface of freshly placed concrete. Colorwise, MASCOCURE CURE & SEAL WB appears milky white in the container but upon application leaves a bluish cast on the concrete for easy visual identification of coverage. MASCOCURE CURE & SEAL WB dries to a transparent medium gloss finish, resists yellowing due to ultraviolet degradation and provides a durable, long lasting finish that offers improved resistance to the damaging effects of freeze-thaw exposure, deicing chemicals and airborne contaminants.

## USAGE

- May be used as cure coat prior to receiving applications of MASCO NORTHWEST BONDBREAKER.
- Cures, seals, hardens and dust-proofs concrete substrates.
- Protects against many oils, acids, salt alkalis, fungus, grease, spalling. Helps to prevent efflorescence.
- Protects aluminum, copper and steel from concrete stains.

## APPLICATION

Ensure application equipment is clean and free of previously used materials. Mix well before each use. MASCOCURE CURE & SEAL WB is ready to use directly from the container. It appears milky white in the container. When first applied it leaves a bluish cast to the surface. It dries to a clear medium gloss finish when properly applied. Shelf life in unopened containers is approximately 1 year. Application can be made with commercial spray cans or power sprayers. Use a spray tip (Chapin 9505E tip) that produces a flow of 1/2 gallon per minute 95° spray under 40 psi of pressure, in a fine fog pattern without spurts and dribbles to form a thin continuous film. Avoid puddling. Should this occur, brush or roll them out.

**NEW CONCRETE:** Spray after final troweling or after surface water sheen has disappeared. If a second coat is desired, first coat must be thoroughly dry, preferably overnight before application of second coat at right angle to first.

Two thin applications are more effective than a single thick coat. Over application will result in the sealer curing improperly and appearing milky white on the surface.

**OLD CONCRETE:** Old concrete must be cleaned and allowed to dry overnight prior to application. All unsightly marks, stains, dirt and dust must be removed from existing concrete. If not, they will be amplified by the transparent finish. Apply in same manner as instructions indicated above for new concrete.

Providing concrete is of sufficient strength, the surface will be ready for normal traffic overnight. Maximum hardness will occur in 7 days. On cured concrete, do not apply during high temperatures in direct sunlight. These conditions cause rapid evaporation which does not allow the film to properly form.

## PACKAGING

5 gallon / 18.9 liter pails  
55 gallon / 208 liter drums

## COVERAGE

Steel Troweled Concrete:  
ASTM-C-309 . . . . .200 – 300 sq ft / gal  
Broom Finished Concrete:  
ASTM-C-309 . . . . .200 sq ft / gal

## CLEANUP

Sprayers and other application equipment can be cleaned with water or MASCO CITRI-CLEAN.

## COMPLIANCES

ASTM-C-309 Type 1, Clear  
Federal EPA V.O.C.

## LIMITATIONS

- Do not apply over bleed water or free standing water.
- Do not apply when the air, material, and surface temperature are expected to fall below 40°F within 4 hours of completed application and / or expected to rain within 12 hours.
- Do not apply heavier than literature recommends or surfaces will remain milky white.
- Do not use on surfaces that receive paints, sealers, epoxy, joint sealants or urethane based coatings without complete removal.
- Only use on colored concrete after 14 days and a test application has been approved or mottling may occur.
- Will rubber tire burn.
- Not recommended for non porous surfaces, i.e. brick, stone, slate, tile, masonry, etc.
- Do not use around swimming pools, hot tubs, or areas exposed to excessive moisture.

- Do not use in areas subject to vapor transmission.
- Will make areas slick when wet.
- Although compatible with many carpet, tile and floor covering adhesives, consult floor covering manufacturer for instructions. A test section is recommended.
- Do not use on a surface that will receive cement mortars, or concrete toppings without complete removal.

## DRYING TIME: (72° F)

Dry to touch . . . . .2-3 hrs.  
Light foot traffic . . . . .4 hrs.  
Normal traffic . . . . .Overnight  
Maximum hardness . . . . .7 days

**DISCLAIMER OF WARRANTIES AND LIMITATIONS OF LIABILITY:** MASONS SUPPLY CO. (Seller) warrants that if any goods supplied prove defective in workmanship or material, that Seller shall replace them or refund their purchase price. THIS WARRANTY IS MADE IN LIEU OF ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND/OR FITNESS WHICH ARE HEREBY DISCLAIMED. IT IS UNDERSTOOD AND AGREED THAT BUYER'S SOLE REMEDY, AND THEREFORE SELLER'S LIABILITY, WHETHER IN CONTRACT, TORT, UNDER ANY WARRANTY, IN NEGLIGENCE, OR OTHERWISE SHALL BE LIMITED TO THE RETURN OF THE PURCHASE PRICE PAID BY PURCHASER OR REPLACEMENT OF ANY DEFECTIVE GOODS SOLD BY SELLER AND UNDER NO CIRCUMSTANCES SHALL SELLER BE LIABLE FOR SPECIAL, INDIRECT OR CONSEQUENTIAL DAMAGES. THE PRICE STATED FOR THE GOODS IS A CONSIDERATION IN LIMITING SELLER'S LIABILITY. Before application, the User shall determine the suitability of the product for his intended use and User assumes all risks and liabilities whatsoever in connection therewith. The terms of this paragraph may not be orally modified. THERE ARE NO WARRANTIES WHICH EXTEND BEYOND THE FACE HEREOF.